

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C10M 135/18	A1	(11) International Publication Number: WO 96/37582 (43) International Publication Date: 28 November 1996 (28.11.96)
(21) International Application Number: PCT/US95/06620 (22) International Filing Date: 24 May 1995 (24.05.95) (71) Applicant (for all designated States except US): EXXON RESEARCH AND ENGINEERING COMPANY [US/US]; 180 Park Avenue, P.O. Box 390, Florham Park, NJ 07932-0390 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): YAMADA, Michiya [JP/JP]; 14-19, Tsurugaoka 1-chome, Ohi-Machi, Iruma-gun, Saitama-ken 356 (JP). ASANO, Satoshi [JP/JP]; 3-8, Negishidai 7-chome, Asaka-shi, Saitama-ken 351 (JP). TOMIZAWA, Hirotaka [JP/JP]; 29-12, Nakaarai 5-chome, Tokorozawa-shi, Saitama-ken 359 (JP). (74) Agents: ALLOCCA, Joseph, J. et al.; Exxon Research and Engineering Company, 180 Park Avenue, P.O. Box 390, Florham Park, NJ 07932-0390 (US).		(81) Designated States: CA, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: LUBRICATING OIL COMPOSITION (57) Abstract A lubricating oil composition comprising a lubricating base oil and containing the following components: sulfoxymolybdenum dithiocarbamate, zinc dialkyldithiophosphate and a mixture of 100 to 50 % by weight of calcium alkylsalicylate and 0 to 50 % by weight of magnesium alkylsalicylate, the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate being from 200 to 1000 ppm (weight basis) of the total weight of the composition, the amount of phosphorus derived from the zinc dialkyldithiophosphate being from 0.04 to 0.15 % by weight of the total weight of the composition, and the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate being from 1 to 10 % by weight of the total weight of the composition. The lubricating oil composition of the invention has excellent antiwear properties, can maintain friction-reducing properties for a prolonged period of time, is excellent in both friction-reducing properties and heat resistance, and is useful as a lubricating oil for internal-combustion engines, automatic transmission gearboxes, dampers, power steering units and the like, particularly useful as a lubricating oil for internal-combustion engines.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

LUBRICATING OIL COMPOSITION

BACKGROUND OF THE INVENTION

The present invention relates to a novel lubricating oil composition. More specifically, the present invention relates to a lubricating oil composition having excellent antiwear properties and friction-reducing properties, capable of maintaining the friction-reducing properties, for a prolonged period of time, useful as a lubricating oil for internal-combustion engines, automatic transmission gearboxes, dampers, power steering units and the like, particularly useful as a lubricating oil for internal-combustion engines.

DISCUSSION OF THE RELATED OIL

Lubricating oils have been used for internal-combustion engines, and for driving units and gears such as automatic transmission gearboxes, dampers and power steering in order to smoothly operate them. In particular, lubricating oils for internal-combustion engines not only lubricate various sliding portions, but also cool the inside of the engines, clean and disperse those products which are produced by combustion, and furthermore prevent the rusting and corrosion of the engines.

In order to meet this requirement, various additives such as an antiwear agent, a metallic detergent, a nonash dispersant and an antioxidant are incorporated into the lubricating oils for internal-combustion engines.

It is particularly important that the lubricating oils ensure the smooth operation of the engines under all operating conditions to prevent the wear and seizure of the engines. The lubricated parts of the engines are, in most cases, under the fluid lubrication condition. However, valve-trains and the top and bottom dead centers of a piston tend to be under the boundary lubrication condition. Antiwear properties under the boundary lubrication condition are generally imparted by the addition of zinc dithiophosphate or zinc dithiocarbamate.

- 2 -

In order to reduce energy lost to friction and to increase fuel economy, a friction modifier is added to lubricating oils. For example, an extreme pressure agent such as a molybdenum compound or a phosphoric ester, or a compound which is an oily agent such as a fatty ester or an alkylamine has been generally used as the friction modifier.

However, while lubricating oil containing such a friction modifier shows the effect of the friction modifier at the outset of the use thereof, it loses the effect when it undergoes oxidative degradation. Namely, the friction-reducing effect of the friction modifier is greatly affected by additives other than the friction modifier, so that it has been difficult for the lubricating oil to maintain, for a long period of time, friction-reducing properties which are shown at the beginning of the operation of an engine.

The present invention has accomplished the objective of developing a lubricating oil (engine oil) which can maintain the effect of reducing friction in engines for a long period of time under these circumstances.

SUMMARY OF THE INVENTION

It has been discovered that a lubricating oil composition having the above described properties is obtained by blending, sulfoxymolybdenum dithiocarbamate having a specific alkyl group, zinc dialkyldithiophosphate having a specific alkyl group, zinc dialkyldithiophosphate having a specific alkyl group, specific alkylsalicylate(s), and, if desired, succinimide containing boron, each in a predetermined amount intra lubricating oil base stock. The present invention has been accomplished on the basis of the above finding.

Namely, the present invention relates to the following lubricating oil compositions:

(1) a lubricating oil composition characterized by comprising a lubricating base oil and additives consisting essentially of:

(a) sulfoxymolybdenum dithiocarbamate containing a hydrocarbon group having 8 to 18 carbon atoms,

- 3 -

(b) zinc dialkyldithiophosphate selected from the group consisting of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms, and a mixture of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms and zinc dialkyldithiophosphate containing a secondary alkyl group having 1 to 18 carbon atoms, and

(c) a mixture of 100 to 50% by weight of calcium alkylsalicylate and 0 to 50% by weight of magnesium alkylsalicylate,

the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate being from 200 to 1000 ppm (weight basis) of the total weight of the composition,

the amount of phosphorus derived from the zinc dialkyldithiophosphate being from 0.04 to 0.15% by weight of the total weight of the composition, and

the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate being from 1 to 10% by weight of the total weight of the composition; and

(2) a lubricating oil composition characterized by comprising a lubricating base oil and additives consisting essentially of:

(a) sulfoxymolybdenum dithiocarbamate containing a hydrocarbon group having 8 to 18 carbon atoms,

(b) zinc dialkyldithiophosphate selected from the group consisting of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms, and a mixture of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms and zinc dialkyldithiophosphate containing a secondary alkyl group having 1 to 18 carbon atoms,

(c) a mixture of 100 to 50% by weight of calcium alkylsalicylate and 0 to 50% by weight of magnesium alkylsalicylate, and

- 4 -

(d) succinimide containing boron,

the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate being from 200 to 1000 ppm (weight basis) of the total weight of the composition,

the amount of phosphorus derived from the zinc dialkyldithiophosphate being from 0.04 to 0.15% by weight of the total weight of the composition,

the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate being from 1 to 10% by weight of the total weight of the composition, and

the amount of boron derived from the succinimide containing boron being from 0.005 to 0.06% by weight of the total weight of the composition.

DETAILED DESCRIPTION OF THE INVENTION

There is no particular limitation on the lubricating base stock oil which is used in the lubricating oil composition of the present invention, and any base oil, such as mineral oil or synthetic oil, which is commonly used for the conventional lubricating basic oils can be used.

Examples of the mineral oil include raffinates which can be obtained by subjecting raw materials for lubricating oils to solvent refining, using an aromatic extraction solvent such as phenol or furfural, hydrogenated oils which can be obtained by subjecting raw materials for lubricating oils to hydrogenation treatment, using a hydrogenation catalyst such as cobalt or molybdenum with a silica-alumina carrier, and lubricating oil fractions which can be obtained by the isomerization of waxes. Suitable base stocks include 60 neutral oil, 100 neutral oil, 150 neutral oil, 300 neutral oil, 500 neutral oil and bright stocks.

- 5 -

Examples of the synthetic oil include poly alpha-olefin oligomers, polybutenes, alkylbenzenes, polyol esters, polyglycol esters, dibasic esters, phosphoric esters and silicone oils. These base oils belonging to mineral oil or synthetic oil can be used either singly or in combination of two or more. Further, a mixture of mineral oil and synthetic oil can also be used.

Those oils which have a viscosity at 100°C of 3 to 20 cSt are preferable as the base oils for use in the lubricating oil composition of the present invention. Of these, hydrocracked oils and wax-isomerized oils which contain 3% by weight or less of aromatics, 50 ppm or less of sulfur and 50 ppm or less of nitrogen are particularly preferred.

As the sulfoxymolybdenum dithiocarbamate to be incorporated into the lubricant oil composition in accordance with the present invention, use may be made of a compound having the following formula [1]:



wherein R^1 and R^2 , are independently a hydrocarbon group with 8 to 18 carbon atoms and may or may not be the same, m and n are a positive integer provided that $m + n = 4$.


Examples of the hydrocarbon group having 8 to 18 carbon atoms, represented by R^1 and R^2 in the general formula [I] include hydrocarbon groups such as an alkyl group having 8 to 18 carbon atoms, an alkenyl group having 8 to 18 carbon atoms, a cycloalkyl group having 8 to 18 carbon atoms, an aryl group having 8 to 18 carbon atoms, an alkylaryl group and an arylalkyl group. The above alkyl and alkenyl groups may be linear or branched. In the lubricating oil composition of the present invention, it is particularly preferable that the hydrocarbon group represented by R^1 and R^2 have 8 carbon atoms.

Specific examples of the hydrocarbon group represented by R^1 and R^2 include octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, octenyl, noneyl,

decenyl, undecenyl, dodecenyl, tridecenyl, tetradecenyl, hexadecenyl, octadecenyl, dimethylcyclohexyl, ethylcyclohexyl, methylcyclohexylmethyl, cyclohexylethyl, propylcyclohexyl, butylcyclohexyl, heptylcyclohexyl, dimethylphenyl, methylbenzyl, phenethyl, naphthyl and dimethylnaphthyl groups.

In the lubricating oil composition of the present invention, either one or two or more sulfoxymolybdenum dithiocarbamates can be used. Further, the sulfoxymolybdenum dithiocarbamate is incorporated into the composition so that the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate can be from 200 to 1000 ppm (weight basis), preferably from 300 to 800 ppm (weight basis) of the total weight of the composition. When the sulfoxymolybdenum dithiocarbamate is incorporated in such an amount that the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate is less than 200 ppm (weight basis) of the total weight of the composition, the effect of improving friction-reducing properties cannot be sufficiently obtained. On the other hand, when the sulfoxymolybdenum dithiocarbamate is incorporated in such an amount that the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate is in excess of 1000 ppm (weight basis) of the total weight of the composition, the effect which is expected from such an amount of the sulfoxymolybdenum dithiocarbamate cannot be obtained, and sludge or the like tends to be brought about.

As the zinc dialkyldithiophosphate to be incorporated into the lubricant oil composition in accordance with the present invention, use may be made of a compound having the following formula [2]:



wherein R³ and R⁴ are independently a primary and secondary alkyl group with 1 to 18, preferably 3 to 18 carbon atoms and may or may not be the same.


In the lubricating oil composition of the present invention, any of the following ones can be used as the zinc dialkyldithiophosphate: zinc dialkyldithiophosphate represented by the general formula [2] in which all of the alkyl

groups are primary; a mixture of zinc dialkyldithiophosphate in which all of the alkyl groups are primary and zinc dialkyldithiophosphate in which all of the alkyl groups is primary and the other alkyl group is secondary; zinc dialkyldithiophosphate in which one of the alkyl groups are secondary; and a mixture thereof.

The primary and secondary alkyl groups represented by R^3 and R^4 in the general formula [2] are propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl and dodecyl groups. However, zinc dialkyldithiophosphate containing a primary or secondary alkyl group having 3 to 12 carbon atoms is preferably used in the lubricating oil composition of the present invention.

In the lubricating oil composition of the present invention, the zinc dialkyldithiophosphate is incorporated so that the amount of phosphorus derived from the zinc dialkyldithiophosphate can be from 0.04 to 0.15% by weight, preferably from 0.06 to 0.12% by weight of the total weight of the composition. When the zinc dialkyldithiophosphate is incorporated into the composition in such an amount that the amount of phosphorus derived from the zinc dialkyldithiophosphate is less than 0.04% by weight of the total weight of the composition, the resulting composition is poor in antiwear properties, in addition, cannot have a satisfactorily low coefficient of friction under the operating conditions of high oil temperatures and low rotational speeds. On the other hand, when the zinc dialkyldithiophosphate is incorporated in such an amount that the amount of phosphorus derived from the zinc dialkyldithiophosphate is in excess of 0.15% by weight of the total weight of the composition, the effect which is expected from such an amount of the zinc dialkyldithiophosphate cannot be obtained.

As the calcium or magnesium alkylsalicylate to be used in the lubricant oil composition in accordance with the present invention, use may be made of a compound having the following formula [3]:



- 8 -

wherein M is calcium or magnesium, and R⁵ and R⁶ are independently alkyl group with 8 to 30 carbon atoms and may or may not be the same.

The alkyl group having 8 to 30 carbon atoms represented by R⁵ and R⁶ in the general formula [3] may be linear, branched or cyclic one. Examples of such an alkyl group include octyl, nonyl, decyl, dodecyl, pentadecyl, octadecyl, eicosyl, docosyl, tricosyl, hexacosyl, triacontyl, dimethylcyclohexyl, ethylcyclohexyl, methylcyclohexylmethyl and cyclohexylethyl groups.

In the lubricating oil composition of the present invention, the alkylsalicylate is incorporated as a mixture of 100 to 50% by weight of calcium alkylsalicylate and 0 to 50% by weight of magnesium alkylsalicylate. The mixture is incorporated in such an amount that the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate is from 0.5 to 10% by weight, preferably from 1 to 6% by weight of the total weight of the composition. When the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate is less than 0.5% by weight of the total weight of the composition, cleaning effect cannot be sufficiently obtained. On the other hand, when the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate is in excess of 10% by weight of the total weight of the composition, the effect which is expected from such an amount of the mixture cannot be obtained, and ash content is rather increased. Such an amount is therefore unfavorable.

In the lubricating oil composition of the present invention, it is preferable to adjust the total base number of the composition to 3 to 10, preferably 4 to 7. The base number of the composition can be determined in accordance with JIS K2501. The total base number of the composition can be adjusted by selecting calcium alkylsalicylate and magnesium alkylsalicylate, each having a proper base number.

Succinimide containing boron can be incorporated into the lubricating oil composition of the present invention, if desired.

The boron/nitrogen ratio regarding the number of the atoms contained in the succinimide containing boron which is used in the lubricating

- 9 -

oil composition of the present invention is from 0.05 to 1.5, preferably from 0.1 to 0.8. When the boron/nitrogen ratio is less than 0.05, the resulting composition cannot have sufficiently-improved friction-reducing properties. On the other hand, when the boron/nitrogen ratio exceeds 1.5, the friction-reducing properties of the resulting composition are impaired.

In the lubricating oil composition of the present invention, the succinimide containing boron is incorporated so that the amount of boron derived from the succinimide containing boron can be from 0.005 to 0.06% by weight, preferably from 0.01 to 0.04% by weight of the total weight of the composition. When the succinimide containing boron is used in such an amount that the amount of boron derived from the succinimide containing boron is less than 0.005% by weight of the total weight of the composition, the resulting composition cannot have sufficiently-improved friction-reducing properties. On the other hand, when the succinimide containing boron is used in such an amount that the amount of boron derived from the succinimide containing boron is in excess of 0.06% by weight of the total weight of the composition, the effect which is expected from such an amount of the succinimide containing boron cannot be obtained.

Various additives which have been usually incorporated into the conventional lubricating oils, such as a metallic detergent, another friction modifier, an antioxidant, a viscosity index improver, a pour point depressant, an anti-foaming agent, other antiwear agent(s), a rust preventive, an ashless dispersant and a corrosion inhibitor, can be added, if necessary, to the lubricating oil composition of the present invention within such a limit that the object of the present invention can be fully attained.

Examples of the metallic detergent include calcium sulfonate, magnesium sulfonate, barium sulfonate, calcium phenate, barium phenate, calcium salicylate and magnesium salicylate. In general, the metallic detergent is used in the composition in an amount of 0.1 to 5% by weight.

Examples of the friction modifier include partial esters of poly-valent alcohols, amines, amides and ester sulfides.

Examples of the antioxidant include amine antioxidants such as alkylated diphenylamines, phenyl-alpha-naphthylamines and alkylated alpha-naphthylamines, and phenolic antioxidants such as 2,6-di-t-butyl-4-methylphenol and 4,4'-methylene-bis(2,6-di-t-butylphenol). In general, such an antioxidant is used in the composition in an amount of 0.05 to 2% by weight.

Examples of the viscosity index improver include those of poly-methacrylate type, polyisobutylene type, ethylene-propylene copolymer type and styrene-butadiene hydrogenated copolymer type. In general, such an improver is used in the composition in an amount of 0.5 to 35% by weight.

Examples of the pour point depressant include polyalkyl-methacrylate, a condensation product of chlorinated paraffin and naphthalene and alkylated polystyrene.

Examples of the anti-foaming agent include dimethyl polysiloxane and polyacrylic acid.

Examples of the antiwear agent include metallic salts of thiophosphoric acid, metallic salts of thiocarbamic acid, sulfur compounds, phosphoric esters and phosphorous esters. In general, this agent is used in the composition in an amount of 0.05 to 5.0% by weight.

Examples of the rust preventive additive include fatty acids, partial esters of alkenyl succinates, fatty acid soaps, alkylsulfonates, fatty polyvalent alcohol esters, fatty amines, paraffin oxides and alkyl polyoxyethylene ethers.

Examples of the ashless dispersant include those of succinimide type, succinamide type, benzylamine type and ester type. In general, such a dispersant is used in the composition in an amount of 0.5 to 7% by weight.

Examples of the corrosion inhibitor include benzotriazole and benzoimidazole.

Examples

The present invention will now be explained more specifically by referring to the following Examples. However, the present invention is not limited by these examples in any way.

The coefficients of friction of the lubricating oil compositions were determined by a reciprocating sliding friction tester [SRV Friction Tester] under the conditions of a frequency of 50 Hz, an amplitude of 3 mm, a load of 25 N, a temperature of 80°C and a test time of 25 minutes.

Examples 1 to 9 and Comparative Examples 1 and 2

The lubricating oil compositions of these examples are those which contain sulfoxymolybdenum dithiocarbamate, zinc dialkyldithiophosphate and alkylsalicylate. Each lubricating oil composition was prepared by blending the components whose type and amount are shown in Table 1 with a base oil (100 neutral oil having a viscosity at 100°C of 4.4 mm/s²). The coefficient of friction of each composition thus obtained was determined right after the composition was prepared, and after the composition was oxidized by being held at 150°C for 72 hours. The results are shown in Table 1.

TABLE 1

	Example											Comparative Example	
	1	2	3	4	5	6	7	8	9	1	2		
Amount of Mo in C ₈ -MoDTC (ppm)	400	800	-	400	400	400	400	400	400	400	400	1	2
Amount of Mo in C ₁₃ -MoDTC (ppm)	-	-	800	-	-	-	-	-	-	-	-	400	400
Amount of phosphorus in C ₈ Zn DTP (primary) (wt%)	0.10	0.10	0.10	0.06	0.07	0.05	0.10	0.10	0.10	-	-	-	-
Amount of phosphorus in C ₃ /C ₆ Zn DTP (secondary) (wt%)	-	-	-	-	0.03	0.05	-	-	-	0.10	-	0.10	-
Calcium C ₁₄ /C ₁₆ /C ₁₈ salicylate (wt%)	3.5	3.5	3.5	3.5	3.5	3.5	2.0	2.0	1.5	3.5	-	-	-
Magnesium C ₁₄ /C ₁₆ /C ₁₈ salicylate (wt%)	-	-	-	-	-	-	-	1.0	1.5	-	-	-	-
Calcium - sulfonate (wt%)	-	-	-	-	-	-	-	-	-	-	-	-	2.0
Succinimide containing boron (wt%)	-	-	-	-	-	-	-	-	-	-	-	-	-
Coefficient of friction	Right after preparation	0.112	0.108	0.111	0.115	0.113	0.115	0.111	0.110	0.141	0.116	0.190	0.145
	After heating at 150°C for 72 hours	0.113	0.110	0.112	0.116	0.115	0.115	0.112	0.112	0.190	0.145		

Note) C₈ - MoDTC: sulfoxymolybdenum - N,N-diethyl-dithiocarbamate
 C₁₈ - MoDTC: sulfoxymolybdenum - N,N-ditridecyl-dithiocarbamate
 C₈ - ZnDTP (primary): zinc di-2-ethylhexylidithiophosphate
 C₃/C₆ ZnDTP (secondary): zinc isopropyl-1-ethyl-butylidithiophosphate

- 13 -

When the lubricating oil compositions of Examples 1 to 9 according to the present invention were used for the determination of the coefficient of friction thereof, it was found that all of the compositions had a low coefficient of friction and excellent friction-reducing properties. Moreover, almost no change was found in the coefficient of friction even after the compositions were heated at 150°C for 72 hours and oxidized. Therefore, it can be understood that the lubricating oil compositions of the invention are excellent in heat resistance. In contrast, in the case of the lubricating oil composition of Comparative Example 1, which was prepared by using only zinc dialkyldithiophosphate having a secondary alkyl group as the zinc dialkyldithiophosphate, the coefficient of friction determined right after the composition was prepared was already high. Moreover, the coefficient of friction became higher after the composition was heated at 150°C for 72 hours and oxidized. It can thus be seen that this comparative composition is poor in both friction-reducing properties and heat resistance. In the case of the lubricating oil composition of Comparative Example 2, which was prepared by using calcium sulfonate instead of alkyl-salicylate, the coefficient of friction became higher after the composition was heated at 150°C for 72 hours and oxidized. It can thus be known that this comparative composition is poor in heat resistance.

Examples 10 to 18 and Comparative Examples 3 and 4

The lubricating oil compositions of these examples are those which contain sulfoxymolybdenum dithiocarbamate, zinc dialkyldithiophosphate, alkyl-salicylate and succinimide containing boron. Each lubricating oil composition was prepared by blending the components whose type and amount are shown in Table 2 with a base oil (100 neutral oil having a viscosity at 100°C of 4.4 mm/s²). The coefficient of friction of each composition thus obtained was determined right after the composition was prepared, and after the composition was oxidized by being held at 150°C for 72 hours. The results are shown in Table 2.

TABLE 2

	Example											Comparative Example	
	10	11	12	13	14	15	16	17	18	3	4		
Amount of Mo in C ₈ -MoDTC (ppm)	400	800	-	400	400	400	400	400	400	400	400		
Amount of Mo in C ₁₃ -MoDTC (ppm)	-	-	800	-	-	-	-	-	-	-	-		
Amount of phosphorus in C ₈ Zn DTP (primary) (wt%)	0.10	0.10	0.10	0.06	0.07	0.05	0.10	0.10	0.10	-	-		
Amount of phosphorus in C ₃ /C ₆ Zn DTP (secondary) (wt%)										-	0.10		
Calcium C ₁₄ /C ₁₆ /C ₁₈ salicylate (wt%)	3.5	3.5	3.5	3.5	3.5	3.5	2.0	2.0	1.5	3.5			
Magnesium C ₁₄ /C ₁₆ /C ₁₈ salicylate (wt%)							1.0	1.5					
Calcium - sulfonate (wt%)													
Succinimide containing boron (wt%)	5	5	5	5	5	5	5	5			2.0		
Amount of boron (wt%)	0.016	0.016	0.016	0.016	0.016	0.016	0.016	0.016	0.016	0.016	5		
Coefficient of friction	0.093	0.095	0.096	0.096	0.094	0.099	0.094	0.096	0.097	0.12	0.095		
	0.093	0.095	0.096	0.098	0.095	0.100	0.096	0.097	0.097	0.172	0.146		
	After heating at 150°C for 72 hours												

Note) C₈ - MoDTC: sulfoxymolybdenum - N,N-dioctyl-dithiocarbamate
 C₁₈ - MoDTC: sulfoxymolybdenum - N,N-ditridecyl-dithiocarbamate
 C₈ - ZnDTP (primary): zinc di-2-ethylhexylidithiophosphate
 C₃/C₆ ZnDTP (secondary): zinc isopropyl-1-ethyl-butylidithiophosphate

- 15 -

The lubricating oil compositions of Examples 10 to 18 according to the present invention, into which succinimide containing boron was incorporated, had a coefficient of friction lower than that of any of the lubricating oil compositions of Examples 1 to 9 which contain no succinimide containing boron, and showed excellent friction-reducing properties. Moreover, almost no change was found in the coefficient of friction even after the compositions were heated at 150°C for 72 hours and oxidized. Therefore, it can be seen that the lubricating oil compositions of the present invention are excellent in heat resistance. In contrast, in the case of the lubricating oil composition of Comparative Example 3, which was prepared by using only zinc dialkyldithiophosphate having a secondary alkyl group as the zinc dialkyldithiophosphate, the coefficient of friction determined right after the composition was prepared was already high, even though succinimide containing boron was incorporated into the composition. Moreover, the coefficient of friction became higher after the composition was heated at 150°C for 72 hours and oxidized. It can thus be seen that this comparative composition is poor in both friction-reducing properties and heat resistance. In the case of the lubricating oil composition of Comparative Example 4, which was prepared by using calcium sulfonate instead of alkylsalicylate, the coefficient of friction became higher after the composition was heated at 150°C for 72 hours and oxidized, even though succinimide containing boron was incorporated into the composition. It can thus be known that this comparative composition is poor in heat resistance.

The lubricating oil compositions of the present invention prepared by blending sulfoxymolybdenum dithiocarbamate having a specific structure, zinc dialkyldithiophosphate, alkylsalicylate, and, if desired, succinimide containing boron with a base oil, therefore, have excellent antiwear properties, can maintain friction-reducing properties for a prolonged period of time, and are excellent in both friction-reducing properties and heat resistance. The lubricating oil compositions of the present invention are thus useful as lubricating oils for internal-combustion engines, automatic transmission gearboxes, dampers, power steering units and the like, particularly useful as lubricating oils for internal-combustion engines.

CLAIMS:

1. A lubricating oil composition characterized by comprising a lubricating base oil and additives consisting essentially of:

(a) sulfoxymolybdenum dithiocarbamate containing a hydrocarbon group having 8 to 18 carbon atoms,

(b) zinc dialkyldithiophosphate selected from the group consisting of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms, a mixture of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms and zinc dialkyldithiophosphate containing a secondary alkyl group having 1 to 18 carbon atoms, zinc dialkyldithiophosphates containing a primary alkyl group having 1 to 18 carbon atoms and a secondary alkyl group having 1 to 18 carbon atoms, and mixture thereof,

(c) a mixture of 100 to 50% by weight of calcium alkylsalicylate and 0 to 50% by weight of magnesium alkylsalicylate,

the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate being from 200 to 1000 ppm (weight basis) of the total weight of the composition,

the amount of phosphorus derived from the zinc dialkyldithiophosphate being from 0.04 to 0.15% by weight of the total weight of the composition, and

the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate being from 0.5 to 10% by weight of the total weight of the composition.

2. A lubricating oil composition characterized by comprising a lubricating base oil and additives consisting essentially of:

(a) sulfoxymolybdenum dithiocarbamate containing a hydrocarbon group having 8 to 18 carbon atoms,

- 17 -

(b) zinc dialkyldithiophosphate selected from the group consisting of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms, a mixture of zinc dialkyldithiophosphate containing a primary alkyl group having 1 to 18 carbon atoms and zinc dialkyldithiophosphate containing a secondary alkyl group having 1 to 18 carbon atoms, zinc dialkyldithiophosphate containing a primary alkyl group containing 1 to 18 carbon atoms and a secondary alkyl group containing 1 to 18 carbon atoms, and mixtures thereof,

(c) a mixture of 100 to 50% by weight of calcium alkylsalicylate and 0 to 50% by weight of magnesium alkylsalicylate, and

(d) succinimide containing boron,

the amount of molybdenum derived from the sulfoxymolybdenum dithiocarbamate being from 200 to 1000 ppm (weight basis) of the total weight of the composition,

the amount of phosphorus derived from the zinc dialkyldithiophosphate being from 0.04 to 0.15% by weight of the total weight of the composition,

the total amount of the calcium alkylsalicylate and the magnesium alkylsalicylate being from 0.5 to 10% by weight of the total weight of the compositions,

the amount of boron derived from the succinimide containing boron being from 0.05 to 0.06% by weight of the total weight of the composition, and the boron/nitrogen ratio regarding the number of atoms containing in the succinimide containing boron is from 0.05 to 1.5.

3. The lubricating oil composition of claim 1 or 2 wherein the lubricating base oil is a hydrocracked oil and/or a wax isomerized oil containing 3% by weight or less aromatics, a sulfur content of 50 ppm or less and a nitrogen content of 50 ppm or less.

4. The lubricating oil composition of claim 1 or 2 wherein the primary or secondary alkyl group of the zinc dialkyldithiophosphate contain 3 to 12 carbon atoms.

5. The lubricating oil composition of claim 1 or 2 having a total base number of 3 to 10.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/06620

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C10M 135/18

US CL : 252/42.7, 46.4, 47.5, 32.7E

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 252/32.7E, 42.7, 46.4, 47.5

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ---- Y	US,A, 5,281,347 (Igarashi et al) 25 January 1994, column 3, lines 25 to column 4, lines 1-25.	1,3-5 ----- 2
Y	US,A, 4,692,256 (Umemura et al) 08 September 1987, column 4, lines 3-end and column 5, lines 5-end.	1-5
Y	US,A, 4,360,438 (Rowan et al) 23 November 1982, column 1, lines 40-66 and column 3, lines 1-24.	1-5
Y	US,A, 3,509,051 (Farmer et al) 28 April 1970, abstract and column 1, lines 28-62 and claims.	1-5

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

20 JULY 1995

Date of mailing of the international search report

23 AUG 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

Margaret B. Medley

Telephone No. (703) 308-2518

Form PCT/ISA/210 (second sheet)(July 1992)*

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US95/06620

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US,A, 4,178,258 (Papay et al) 11 December 1979 ALL.	1-5
Y	US,A, 3,254,025 (LeSuer) 31 May 1966, column 2, lines 6-40; column 21, lines 73 to column 1-64.	2-5
Y	US,A, 4,846,983 (Ward, Jr) 11 July 1989, column 1, lines 37 to column 2, lines 1-20 and Tables I and II.	1-5

Form PCT/ISA/210 (continuation of second sheet)(July 1992)*